


Sample Name: Poly(isobornyl methacrylate)

Sample #: p3632F4-iBMA

Structure:




Composition:

$M_n \times 10^3$	PDI
81.0	1.35

Synthesis Procedure:

Poly(isobornyl methacrylate) is obtained by living anionic polymerization of isobornyl methacrylate. The reaction scheme used for the polymer synthesis is shown below:




Characterization:

The molecular weight and polydispersity index (PDI) of Poly(isobornyl methacrylate) are obtained by size exclusion chromatography.

Solubility:

Poly(isobornyl methacrylate) is soluble in THF, $CHCl_3$, toluene and dioxane. The polymer precipitates from hexanes, methanol and ethanol.

SEC of Homopolymer:



Size exclusion chromatograph of Poly isobornyl metacrylate:

$M_n=81000$, $M_w=110,000$ $PI=1.35$