


Sample Name: Deuterated Polystyrene (d₈)

Sample #: P3645-dPS

Structure:




Composition:

Mn x 10 ³	PDI
9.0	1.2

Synthesis Procedure:

Deuterated polystyrene-d₈ is obtained by living anionic polymerization of styrene-d₈ as illustrated below:



Characterization:


The molecular weight and polydispersity index (PDI) are obtained by size exclusion chromatography (SEC) in THF. SEC analysis was performed on a Varian liquid chromatograph equipped with refractive and UV light scattering detectors from Viscotek Co. Three SEC columns from Supelco (G6000-4000-2000 HXL) were used.

Solubility:

Deuterated polystyrene-d₈ is soluble in DMF, THF, toluene and CHCl₃. It precipitates from methanol, ethanol, water and hexanes.

SEC of Homopolymer:

P3645-dPS



Size exclusion chromatograph of deuterated polystyrene (d₈):

M_n=9000, M_w=10800, PI=1.2