




Product Profile

Identification

Product Name: Amino Terminated Polystyrene

Product Lot Number: P3956-SNH2


Chemical Architecture:



Composition:

Mn (g/mole)	11,000
Mw (g/mole)	12,000
Mw/Mn	1.10
Primary Amino group test using ninhydrin	Blue color pass

Method of Synthesis ω -amino terminated polystyrene was synthesized by anionic living polymerization with different end-grouping strategies. The reaction schemes are shown below:



Solubility in different solvents:


THF	√	Methanol	X
CHCl ₃	√	Hexane	X
Toluene	√		

Validation of Architecture

A. Gel Permeation Chromatography (GPC), SEC Profile:

The molecular weight and polydispersity index of this polymer were determined by size exclusion chromatography (SEC) using a Varian liquid chromatograph equipped with a UV and refractive index detector. However, amino terminated polystyrene was found to interact with chromatography columns and therefore the amino group was protected by reaction with 1-naphthyl isocyanate before GPC analysis. Removal of the protecting group was confirmed by UV spectroscopy and the degree of functionality was confirmed by titration with HClO_4 using crystal violet as the indicator.

P3956-SNH2



Size exclusion chromatography of monoamino terminated terminated polystyrene.
(NH_2 group end capped with 1-naphthyl isocyanate)

$M_n=11000$, $M_w=12000$, $PI=1.10$, functionality=0.98.