


**Sample Name:** Poly(t-butyl acrylate-b-methyl methacrylate)

**Sample #:** P432-tBuAMMA

**Structure:**



**Composition:**

Mn x 10 <sup>3</sup> tBuA-b-MMA	PDI
18.4-b-3.1	1.03
T <sub>g</sub> for MMA block	63°C
T <sub>g</sub> for tBuA block	38°C

**Synthesis Procedure:**

Poly(t-butyl acrylate-b-methyl methacrylate) is prepared by living anionic polymerization with sequence addition of t-butylacrylate followed by methyl methacrylate in THF using an RLi/LiCl adduct.

**Characterization:**


An aliquot of the anionic poly(t-butyl acrylate) block was terminated before addition of methyl methacrylate and analyzed by size exclusion chromatography (SEC) to obtain the molecular weight and polydispersity index (PDI). The final block copolymer composition was calculated from <sup>1</sup>H-NMR spectroscopy by comparing the peak area of the methyl methacrylate protons at about 3.6 ppm with the peak area of t-butyl acrylate protons at about 1.43 ppm. Copolymer PDI is determined by SEC.

Thermal analysis of the sample was carried out using a differential scanning calorimeter (TA Q100) at a heating rate of 10°C/min. The inflection glass transition temperature (T<sub>g</sub>) has been considered.


**Solubility:**

Poly(t-butyl acrylate-b-methyl methacrylate) is soluble in THF, CHCl<sub>3</sub>, toluene, dioxane. The polymer can precipitate from ethanol/water or methanol/water mixtures.

**SEC of the block copolymer:**



**Thermogram for PtBuA block polymer**



**Thermogram for PMMA block polymer**

