


Sample Name:

Poly(styrene-b-butadiene_(rich in 1,4 addition)-b-methylmethacrylate)

Sample #: **P4869-SBdMMA**

Structure:




Composition:

| | |
|--------------------------------------|-----|
| Mn x 10 ³ S-b-Bd-b-MMA | PDI |
| 72.0-4.0-162.0 | 1.5 |

Synthesis Procedure:

By living anionic polymerization with sequence addition of styrene, butadiene (Bd), then methyl methacrylate (MMA). The scheme of the reaction is illustrated below:



Characterization:


First Block: Size exclusion chromatography (SEC): Varian liquid chromatograph equipped with UV and refractive detector. SEC columns from Supelco were used with THF as the eluent. The columns were calibrated with monodisperse polystyrene. The molecular weights and the polydispersity index were calculated.

Second and Third Block: The chemical composition was extracted from proton NMR, which was recorded from Varian 500MHz instrument using CDCl₃ as solvent. The molecular weights of second and third block were calculated based on the molecular weight of other blocks and the chemical composition. The polydispersity index of block copolymer was obtained by SEC as described above.


Solubility:

Polymer is soluble in THF, toluene, and CHCl₃. The polymer readily precipitates from hexanes, ether and water.

¹H-NMR Spectrum of the product



P4869-SBdMMA



Size exclusion chromatography of polystyrene-b-butadiene_(1,4 rich addition)-b-methylmethacrylate)

- First block Poly styrene, M_n=72000, M_w=76500, PI=1.06
- Second block Poly(styrene-b- polybutadiene):PS(72000)-b-PBd(4000), PI=1.06
- Final Triblock copolymer: PS(72000)-b-PBd(4000)-b-PMMA(162000), PI=1.5

Composition from ¹H NMR