


Sample Name: Poly(n-nonyl acrylate)

Sample #: P4896-nNA

Structure:





Composition:

$M_n \times 10^3$	PDI
29.0	1.10

Synthesis Procedure:

Poly(n-nonyl acrylate) is obtained by the transesterification reaction with poly tert-butylacrylate in the presence of 1-nonanol. The reaction scheme is shown below:



Characterization:


The molecular weight and polydispersity index (PDI) are obtained by size exclusion chromatography (SEC) in THF. SEC analysis was performed on a Varian liquid chromatograph equipped with refractive and UV light scattering detectors. Three SEC columns from Supelco (G6000-4000-2000 HXL) were used with triple detectors from Viscotek Co.

Solubility:

Poly(n-nonyl acrylate) is soluble in THF, toluene and CHCl_3 . This polymer precipitates from ethanol and methanol containing 10-15% water.

SEC of the Homopolymer:

P4896-nNA



Size Exclusion Chromatography of Poly(n-nonyl acrylate):

$M_n = 29000$, $M_w = 32000$, $M_w/M_n = 1.10$