


**Sample Name:**  $\alpha$ - Hydroxy  $\omega$ - Bromo  
Terminated Poly(methyl methacrylate)

**Sample #:** P5506-MMAOHBr

**Structure:**



**Composition:**

Mn x 10 <sup>3</sup>	PDI
2.5	1.10
Iso:hetero:syndio:	7:19:74 ratio
OH functionality	>99%
Br functionality	>98%

**Synthesis Procedure:**

$\alpha$ - Hydroxy  $\omega$ - Bromo terminated poly(methyl methacrylate) was prepared by anionic polymerization.

**Characterization:**

The molecular weight and polydispersity index (PDI) are obtained by size exclusion chromatography (SEC) in THF. SEC analysis was performed on a Varian liquid chromatograph equipped with refractive and UV light scattering detectors. Three SEC columns from Supelco (G6000-4000-2000 HXL) were used with triple detectors from Viscotek Co.

**Solubility:**

Polymer is soluble in DMF, THF, toluene and CHCl<sub>3</sub>. It precipitates from methanol, ethanol, water and hexanes

**HNMR of the Polymer:**

