



Sample Name: Deuterated Poly(methylacrylate) Ester group protonated

Sample #: P5659-d3MA

Structure:



D NMR of the monomer:



Composition:

Mn x 10 ³	PDI
4.0	1.6


Characterization:

The molecular weight and polydispersity index (PDI) are obtained by size exclusion chromatography (SEC) in THF. SEC analysis was performed on a Varian liquid chromatograph equipped with refractive and UV light scattering detectors. Three SEC columns from Supelco (G6000-4000-2000 HXL) were used with triple detectors from Viscotek Co.

Solubility:


Deuterated Poly(methyl acrylate) is soluble in THF, CHCl₃, Toluene.

HNMR of the monomer:



SEC of Sample:

P5659-d3PMA (vinyl group deuterated)



Size Exclusion Chromatography of Poly(methyl acrylate-d3)

M_n=4,000, M_w=6,400, M_w/M_n=1.6

References:

1. Ph. Teyssié, Ph. Bayard, R. Jerome, **S. K. Varshney**, and J. S. Wang, *35th IUPAC International Union of Pure & Applied Chemistry International Symposium on Macromolecules*” 1994, 67.
2. R. Fayt, R. Forte, C. Jacobs, R. Jerome, T. Ouhadi, Ph. Teyssié and **S. K. Varshney**, *Macromolecules*, 1987, 20, 1442-1444.
3. Jerome, R. Forte, **S. K. Varshney**, R. Fayt, and Ph. Teyssié, "The Anionic Polymerization of Alkylacrylates:A Challenge" in the Recent Advances in Mechanistic and Synthetic Aspects of Polymerization: M. Fontanaille and A. Guyot Ed., NATO ASI Series C 215,101 (1987), CA Vol. 108, 12, 094992.
4. Ph. Teyssié, R. Fayt, C. Jacobs, R. Jerome, L. Leemans, and **S. K. Varshney** *Am. Chem. Soc.,Polym. Prepr.* 1988, 28, 2, 52-53