


Sample Name: Poly(t-butyl acrylate)

Sample #: P10512-tBuA

Structure:



Composition:

Mn x 10 ³	PDI
96.5	1.3

Synthesis Procedure:

Poly(t-butyl acrylate) is obtained by anionic process.

Characterization:

The molecular weight and polydispersity index (PDI) are obtained by size exclusion chromatography (SEC) in THF. SEC analysis was performed on a Varian liquid chromatograph equipped with refractive and UV light scattering detectors. Three SEC columns from Supelco (G6000-4000-2000 HXL) were used with triple detectors from Viscotek Co.


Solubility:

Poly(t-butyl acrylate) is soluble in THF, hexanes (low MW), toluene and CHCl₃. This polymer precipitates from ethanol and methanol containing 10-15% water.


SEC of Sample:

Sample ID: P10512-tBuA


Concentration (mg/mL)	3.5258
Sample dn/dc (mL/g)	0.0512
Method File	PS80K-Oct-0000.vcm
Column Set	3x PL 1113-6300
System	System 1



Sample	Mn (Da)	Mw(Da)	Mp (Da)	Mw/Mn	IV (dL/g)
P10512-tBuA_2011-10-24_15:56:07_01.vdt	96,409	133,494	121,330	1.385	0.7532



Tg of poly t-butyl acrylate as function of molecular weight



References:

1. Ph. Teyssie, Ph. Bayard, R. Jerome, **S. K. Varshney**, and J. S. Wang, *35th IUPAC International Union of Pure & Applied Chemistry International Symposium on Macromolecules* 1994, 67.
2. R. Fayt, R. Forte, C. Jacobs, R. Jerome, T. Ouhadi, Ph. Teyssie and **S. K. Varshney**, *Macromolecules*, 1987, 20, 1442-1444.
3. Jerome, R. Forte, **S. K. Varshney**, R. Fayt, and Ph. Teyssie, "The Anionic Polymerization of Alkylacrylates:A Challenge" in the *Recent Advances in Mechanistic and Synthetic Aspects of Polymerization*: M. Fontanaille and A. Guyot Ed., NATO ASI Series C 215, 101 (1987), CA Vol. 108, 12, 094992.
4. Ph. Teyssie, R. Fayt, C. Jacobs, R. Jerome, L. Leemans, and **S. K. Varshney** *Am. Chem. Soc., Polym. Prepr.* 1988, 28, 2, 52-53