


Sample Name: **Poly(methyl methacrylate)**  
*Different Microstructure*

Sample #: **P6064-MMA**

**Structure:**



**Composition:**

$M_n \times 10^3$	PDI
30.4	2.10
Syndio : Hetero : Isotactic	64 : 33 : 3

**Synthesis Procedure:**

Poly(methyl methacrylate) is obtained by free radical polymerization (ATRP) using CuBr as catalyst.

**Characterization:**

Tacticity of the polymer was determined by  $^1\text{H}$  NMR. The molecular weight and polydispersity index (PDI) were obtained by size exclusion chromatography (SEC) in THF. SEC analysis was performed on a Varian liquid chromatograph equipped with refractive and UV light scattering detectors. Three SEC columns from Supelco (G6000-4000-2000 HXL) were used with triple detectors from Viscotek Co.

Thermal analysis of the samples was carried out using a differential scanning calorimeter (TA Q100) at a heating rate of  $10^\circ\text{C}/\text{min}$ . The inflection glass transition temperature ( $T_g$ ) of the sample has been considered.


**Solubility:**

The polymer is soluble in THF,  $\text{CHCl}_3$ , toluene and dioxane. The polymer precipitates from cold methanol and ethanol.


**$T_g$  vs MW for selected atactic PMMA:**

$M_n \times 10^3$	$T_g (^\circ\text{C})$	$M_n \times 10^3$	$T_g (^\circ\text{C})$
1.1	51	36	98
2.5	76	55	111
5.0	91	70	107
15	101	127	115
19	107	230	114
29	96	700	121

**$^1\text{H}$  NMR spectrum of PMMA:**



**SEC elugram of PMMA homopolymer:**  
**P6064-MMA**



Size Exclusion Chromatography of poly(methyl methacrylate)-Atactic:  
 —  $M_n = 30400$ ,  $M_w = 63800$ ,  $M_w/M_n = 2.10$

**DSC:**

$T_g$  of atactic poly methyl methacrylate as function of molecular weight

