


Sample Name: Polylactide

Sample #: P6463B-LA (DL-Form)

Structure:




Composition:

$M_n \times 10^3$	PDI
310.0	1.85
$T_g (^{\circ}\text{C})$	55

Synthesis Procedure:

The polymerization of D/L-Lactide was initiated with an Tin catalyst and the reaction was carried out without solvent.



Characterization:

The molecular weight and polydispersity index (PDI) are obtained by size exclusion chromatography with light scattering and viscometer detectors.


Thermal analysis:

Thermal analysis of the samples was carried out on a TA Q100 differential scanning calorimeter at a heating rate of 10°C/min. The midpoint of the slope change of the heat flow plot of the second heating scan was considered as the glass transition temperature (T_g).

Solubility:

Poly(DL-lactide) is soluble THF, CHCl_3 and CH_2Cl_2 . The polymer is insoluble in methanol, hexane and ether.

SEC of Homopolymer:



DSC thermogram for the sample:

