


**Sample Name:** UV Cleavable (at 350nm)  
**Poly(ethylene oxide-b-THF methacrylate)**

**Sample #:** P6842-EOTHFMACleav

**Structure:**



**Composition:**

Mn x 10 <sup>3</sup> PEO-b-PTHFMA	PDI
7.0-b-60.0	1.40
MA rich in atactic microstructure	

**Synthesis Procedure:**

Proprietary procedure.


**Characterization:**

PEG-Br and final block copolymer were analyzed by size exclusion chromatography (SEC) to obtain the molecular weight of PEG and polydispersity index (PDI) for both PEG and block copolymer. The final block copolymer composition was calculated from <sup>1</sup>H-NMR spectroscopy by comparing the peak area of the ethylene oxide protons at about 3.6 ppm with the α-methyl protons of MA at about 1.0 ppm.


**Solubility:**

Poly(ethylene oxide-b-THFMA) is soluble in THF, acetone, and chloroform and it precipitates out in hexane or methanol.

**<sup>1</sup>H-NMR Spectrum of the macroinitiator:**



**<sup>1</sup>H-NMR Spectrum of the block copolymer:**



**SEC of the block copolymer:**

**P6842-EOTHFMA cleav**

