


Sample Name:

Poly(4-styrene sulfonic acid-Sodium salt)

In dialysed form or undialysed form

Sample #: **P742-USSO3Na** Undialysed form

Structure:




Composition:

Mn x 10 ³	PDI
1017.2	1.12
C;H;S	37.28:5.42:14.30
Degree of sulfonation	>85%

Synthesis Procedure:

Poly(styrene sulfonic acid) is obtained from the sulfonation of polystyrene. Polystyrene was obtained by anionic living polymerization. The molecular distribution of the obtained polystyrene sulfonic acid remains same as of the parent polymer. Furthermore the H NMR and FTIR spectroscopy of the polymer shows the sulfonation is predominately at para position of the phenyl group. The reaction scheme is illustrated below:



Characterization:

Size exclusion chromatography (SEC) was carried out on a Varian liquid chromatograph equipped with a refractive detector. For the precursor polystyrene, two columns from Supelco (G4000-2000 HXL) were used with THF as the eluent. The columns were calibrated with monodisperse polystyrene standards. The molecular weight and the polydispersity indice were calculated. For polystyrene sulfonic acid, a column from Supelco (G5000 PWXL) was used with 0.1 NaNO₃ /water as the eluent.


The degree of sulfonation was determined by acid/base titration and by elemental analysis.

Solubility:

Poly(styrene sulfonic acid) is soluble in methanol, water and precipitated out from the hexane, THF, toluene.

SEC of Homopolymer:

P742-USSO₃Na



Size exclusion chromatograph of poly(styrene sulfonic acid-Sodium salt)
Polystyrene precursor

$M_n=1017200$, $M_w=1139000$ PI=1.12
degree of Sulfonation : >85%

HNMR Spectrum of the Polymer:

