


Sample Name: Poly(n-hexyl methacrylate)

Sample #: P8126-nHMA

Structure:




Composition:

Mn x 10 ³	PDI
15.0	1.4
T _g (°C)	-13

Synthesis Procedure:

Poly(n-hexyl methacrylate) is obtained by living anionic or GTP polymerization of n-hexyl methacrylate. The reaction scheme used for the polymer synthesis is shown below:



Characterization:

The molecular weight and polydispersity index (PDI) of Poly(n-hexyl methacrylate) are obtained by size exclusion chromatography.

Thermal analysis of the sample:


Thermal analysis of the samples was carried out on a TA Q100 differential scanning calorimeter at a heating rate of 10°C/min. The midpoint of the slope change of the heat flow plot of the second heating scan was considered as the glass transition temperature (T_g).

Solubility:

Poly(n-hexyl methacrylate) is soluble in THF, CHCl₃, toluene and dioxane. The polymer precipitates from cold methanol and ethanol.

SEC of Homopolymer:

P8126-nHMA



DSC thermogram for the polymer:

