


Sample Name: Poly(styrene-b- tert.butylacrylate)

Sample #: P8294-StBuA

Structure:




Composition:

Mn x 10 ³ S-b-tBuA	PDI
45.0-b-49.0	1.09

Synthesis Procedure:

Poly(styrene-b-tert.acrylate) is prepared by living anionic polymerization in THF at -78 °C using sec.BuLi initiator adduct with α -methyl styrene in the presence of LiCl. tert.butyl acrylate (tBuA) monomer was added after dilution in THF. For further details please see our published articles.¹⁻⁵ The scheme of the reaction is illustrated below:



Characterization:


An aliquot of the anionic polystyrene block was terminated before addition of tBuA and analyzed by size exclusion chromatography (SEC) to obtain the molecular weight and polydispersity index (PDI). The final block copolymer composition was calculated from ¹H-NMR Copolymer Mw/Mn is determined by SEC.

Solubility:


Poly(styrene-b-tert.butylacrylate) is soluble in THF, toluene, dioxane and CHCl₃. This polymer readily precipitates from methanol, ethanol, hexanes and water.

SEC of Sample :

P8294-StBuA



HNMR of the Polymer:



References for further information:

1. S. K. Varshney, R. Fayt, Ph. Teyssie, and J.P. Hautekeer US Patent 5,264,527 (1993)
2. Ph. Teyssie, R. Fayt, **S. K. Varshney**, and C. Jacobs Eur. Pat. Appl., Jan 16, 1991 Eur.Pat.408420
Patent Assignees- Atochem S.A France. CA. Vol 114, 26, 247998." Star Block Copolymers based on Acrylates and Methacrylates and their Manufacture process".
3. Ph.Teyssie, R. Fayt, and **S. K. Varshney**, Eur. Pat. Appl. Dec. 12, 1990. Eur. Pat.402204
Patent Assignees-Norsolor S.A. France. CA Vol 114, 20, 186314."Catalyst for the the Anionic Living Polymerization (Meth)acrylates".
4. **S. K. Varshney**, R. Fayt and Ph. Teyssie Eur. Pat. Appl. Dec. 12, 1990. Eur. Pat. 402219
Patent Assignees- Norsolor S.A France. CA Vol 114, 22, 208036. "Procedure and Anionic Polymerization Catalyst for Acrylic Monomers".
5. **S. K. Varshney**, R. Fayt, Ph. Teyssie, and J. P. Hautekeer, Eur. pat. Appl. Jan 16, 1991. Eur. Pat. 408429
Patent assignees-Norsolor S.A France. CA Vol. 115, 10, 094237."Acrylic Triblock Copolymers and their Preparation and use as Rubbers
6. Ph. Teyssie, Ph. Bayard, R. Jerome, S. K. Varshney, and J. S. Wang, 35th IUPAC International Union of Pure & Applied Chemistry International Symposium on Macromolecules" 1994, 67.
7. Ph. Teyssie, R. Fayt, J. P. Hautekeer, C. Jacobs, R. Jerome, L. Leemans and S. K. Varshney Makromolekular Chemie, Macromol. Symp., 1990, 32,61-73.
8. S. K. Varshney, J. P. Hautekeer, R. Fayt, R. Jerome, and Ph.Teyssie Macromolecules, 1990, 23, 2618-2622.