

Sample Name:


α - ω - Dicarboxy Terminated Poly(t-butyl acrylate)

SEC of Sample:

P8821-tBuA2COOH

Sample #: **P8821-tBuA2COOH**

Structure:




Composition:

$M_n \times 10^3$	PDI	COOH functionality %
5.5	1.17	1.95

Synthesis Procedure:

Carboxy Terminated Poly(t-butyl acrylate) is synthesized by living anionic polymerization of methyl methacrylate using a bifunctional initiator (oligomer \square -methylstyrene lithium) in THF followed by termination with dry ice.



Characterization:

The molecular weight and polydispersity index of this polymer were determined by size exclusion chromatography (SEC) before inclusion of the CO₂H function using a Varian liquid chromatograph equipped with a UV and refractive index detector. The functionality of polymer was determined by the titration with NaOH, using phenolphthalein as the indicator.

Solubility: Soluble in THF, CHCl₃.

