


Sample Name: Poly(styrene-b-lactide)

Sample #: P8853-SLA (LA is DL form)

Structure:




Composition:

Mn x 10 ³ S-b-LA	Mw/Mn (PDI)
27.0-b-1.0	1.09

Synthesis Procedure:

Poly(styrene-b-lactide) is prepared by living anionic polymerization in sequential addition of styrene followed by lactide monomer or by taking the OH end functionalized polystyrene and using co-ordination polymerization process. The scheme of the reaction is illustrated below:




Characterization:

The block polymer was analyzed by size exclusion chromatography (SEC) to estimate the molecular weight and polydispersity index (PDI). Further, the copolymer composition was calculated from ¹H-NMR spectroscopy by comparing the peak area of the polystyrene protons at about 6.3-7.2 ppm with the lactide protons at 5.2 ppm. Copolymer PDI was determined by SEC.

Solubility:


Poly(styrene-b-lactide) is soluble in chloroform, THF, and toluene.

¹H-NMR Spectrum of the block copolymer:



SEC of Sample of the block copolymer:

P8853-St-LA (DL -form)



Size Exclusion chromatography of poly (styrene-b- L -lactide):

- Polystyrene, M_n=27,000, M_w=29,000, PI=1.07
- Block Copolymer from Light scattering
PS(27,000)-b-LA(1000), PI=1.09 Composition from H NMR


Thermal analysis of the sample# P8853-SLA

Thermal analysis of the block polymer was carried out on a TA Q100 differential scanning calorimeter at a heating rate of 10°C/min. The midpoint of the slope change of the heat flow plot of the second heating scan was considered as the glass transition temperature (T_g).

Thermal analysis results at a glance

T_g for PLA block	T_g for PS block
07°C	89°C

Thermogram for PLA block:



For PS block

