Sample Name: Poly(α-methylstyrene-b-4-vinyl pyridine)

Sample #: P9118-aMeS4VP

Structure:

Composition:

Mn x 10³ PaMeS-b-4VP	PDI
13.0-b-24.0	1.10
T_g for αMeS block: 170°C	T_g for 4VP block: 150°C

Synthesis Procedure:

Poly(styrene-b-4-vinyl pyridine) is prepared by living anionic polymerization in THF or THF–DMF solvent mixtures at –78 °C. Polystyrene macroanions were end capped with a unit of diphenyl ethylene (DPE) before adding 4-vinylpyridine (4VP) monomer. For further details please see our published articles.[1,2]

Characterization:

An aliquot of the anionic polystyrene block was terminated before addition of 4-vinyl pyridine and analyzed by size exclusion chromatography (SEC) in DMF to obtain the molecular weight and polydispersity index (PDI). The block copolymer composition was then calculated from [1]H-NMR spectroscopy by comparing the peak area of the two aromatic 4-VP protons at about 8.5 ppm with the peak area of the aromatic protons of polystyrene at 6.3-7.2 ppm. The composition of the block copolymer can also be determined by titration in acetic acid/HClO4 using crystal violet indicator. Copolymer PDI is determined by SEC.

Thermal analysis of the samples was carried out using a differential scanning calorimeter (TA Q100) at a heating rate of 10°C/min. The inflection glass transition temperature (T_g) of the sample has been considered.

Solubility:

Poly(styrene-b-4-vinyl pyridine) is soluble in DMF, CHCl3. The polymer can also be solubilized in THF depending on its chemical composition. The polymer readily precipitates from hexanes and diethyl ether.

[1]H-NMR Spectrum of Sample:

SEC of Sample

P9118-aMeS4VP

—— Poly a methylstyrene, M_n=13000, M_w=13800, PI=1.06
—— Block Copolymer PaMeS(13000)-b-P4VP(5000), PI=1.10

DSC thermogram for the block polymer:

References:

(1). S. K. Varshney, X. F. Zhong & A. Eisenberg *Macromolecules,* **1993**, 26, 701-706.
(2). Z.Gao, S. K. Varshney, S. Wong, A. Eisenberg *Macromolecules,* **1994**, 27, 7923-7927.