


Sample Name: Hydroxy Terminated Poly(methylmethacrylate-*b*-styrene) with Bromide terminal end towards polystyrene block

Sample #: P9362-HOMMASBr



Composition:

Mn x 10 ³ MMA- <i>b</i> -St	Mw/Mn (PDI)	PMMA microstructure (Iso:hetero:syndio)
2.5- <i>b</i> -25.0	1.5	3: 18: 79
T _g for PS block: 97°C		T _g for MMA block: -

Synthesis Procedure:

Polymer is obtained by combination of anionic and controlled radical process using different ligand system.


Characterization:

Polymer was analyzed by size exclusion chromatography (SEC) to obtain the molecular weight and polydispersity index (PDI). The final block copolymer composition was calculated from ¹H-NMR spectroscopy.


Thermal analysis:

Thermal analysis of the samples was carried out on a TA Q100 differential scanning calorimeter at a heating rate of 10°C/min. The midpoint of the slope change of the heat flow plot of the second heating scan was considered as the glass transition temperature (T_g).


¹H NMR spectrum HOMMA-Br



HNMR of the Polymer:



SEC profile of the block copolymer



DSC thermogram for the diblock polymer:

