


Sample Name:**Poly(Styrene-b-isoprene-b-2-vinylpyridine)****Sample #: P9402-Sip2Vp****Structure:****Composition:**

Mn x 10 ³ S-b-IP-b-2VP	PDI
40.0-b-33.0-b-87.0	1.15
Microstructure for IP block	Rich in 1,4 addition

Synthesis Procedure:

By living anionic polymerization with sequence addition of styrene then isoprene (polymerization in a polar solvent), followed by addition of 2VP monomer.



Characterization:

First Block: Size exclusion chromatography (SEC): Varian liquid chromatograph equipped with UV and refractive detector. SEC columns from Supelco were used with THF as the eluent. The columns were calibrated with monodisperse polystyrene. The molecular weights and the polydispersity index were calculated.

Second and Third Block: The chemical composition was extracted from proton NMR, which was recorded from Varian 500MHz instrument using CDCl₃ as solvent. The molecular weights of second and third block were calculated based on the molecular weight of other blocks and the chemical composition. The polydispersity index of block copolymer was obtained by SEC as described above.

Solubility:

Polymer is soluble in THF, toluene, and CHCl₃. The polymer readily precipitates from cold hexanes/ethanol mixture. .

¹H-NMR Spectrum of the polymer:**SEC for the polymer:****P9402-SIP2VP**

Size Exclusion Chromatography :

- First PS block, M_n=40000 Mw: 43500 M_w/M_n=1.08
- PS-IP, diblock PS(40000)-b-PIP(33000), M_w/M_n=1.10
- Triblock PS(40000)-b-PIP(33000) -b-P2VP(87000) M_w/M_n=1.15


Thermal Analysis of sample# P9402-SIp2VP

Thermal analysis of the samples was carried out on a TA Q100 differential scanning calorimeter at a heating rate of 10°C/min. The midpoint of the slope change of the heat flow plot of the second heating scan was considered as the glass transition temperature (T_g).

Thermal analysis results at a glance

For PS block:	For 2VP block:	For PIP block:
T_g : -	T_g : 100 °C	T_g : -68°C

DSC thermogram for PIP block:



DSC thermogram for 2VP block:

