


Sample Name:

Poly(N-isopropylacrylamide -b- NN-dimethylaminoethylmethacrylate)

Sample #: **P16063F2-NIPAMDMAEMA**

Structure:



Composition:

Mn x 10 ³ PNIPAM-b-NNDMAEMA	53.0-b-67.0
PDI	1.50

Dp for each block PNIPAM-b-NNDMAEMA	469-b-426
--	-----------

Synthesis Procedure: Poly(N-isopropylacrylamide -b- NN-dimethylaminoethylmethacrylate) was synthesized by atom transfer radical polymerization.


Characterization:

The molecular weight and polydispersity index (PDI) of diblock copolymer were obtained by size exclusion chromatography (SEC). The composition of the polymer was characterized by NMR.


Solubility:

The polymer is soluble in THF, DMF, Acetone.

ATRP reagent used for polymerization:




¹H NMR Spectrum of the block copolymer:



SEC elugram of the polymer:

P16063F2-NIPAMDMAEMA

Conc (mg/mL)	1.4944
dn/dc (mL/g)	0.0800
Method	PS80k August-08-2016-0000.vcm
Solvent	DMF w 0.023M LiBr
Column	PSS



Sample	Mn	Mw	Mp	Mw/Mn	IV
P16063-A_01.vcl	120,037	180,809	139,019	1.506	0.4780