


Sample Name:

Amino end functionalized Poly(ethylene oxide-b-caprolactone)

Sample #: P40576A- NH2EGCL

Structure:



Composition:

Mn x 10 ³ Phtha- EG-b-PCL	PDI	NH2 functionality
5.0-b-6.5	1.18	>99%


Synthesis Procedure:

The polymer was synthesized by combination of anionic and coordination ring opening polymerization process.

Characterization:

The product was characterized by size exclusion chromatography (SEC) and ¹H NMR.

¹H NMR spectrum of the diblock copolymer:



SEC elugram of the block copolymer:

P40576A- NH2EGCL

