


**SEC elugram of the polymer:**  
**P40817A**

Conc	1.6996
dn/dc	0.1650
Solvent	DMF w 0.023M LiBr
Flow Rate	0.7000
Method	PS80k_2017-11-07-0000.vcm



Sample	Mn	Mw	Mp	Mw/Mn	IV
p40817A_01.vdt	203,230	275,211	268,430	1.354	76.9379