


Sample Name: Poly (t-butyl acrylate)

Sample #: P41114-tBuA

**Structure:**



**Composition:**

$M_n \times 10^3$	PDI
29.0	1.28

**Synthesis Procedure:**

Poly(t-butyl acrylate) is obtained by anionic polymerization process.

**Characterization:**

The molecular weight and polydispersity index (PDI) are obtained by size exclusion chromatography (SEC) in THF. SEC analysis was performed on a Varian liquid chromatograph equipped with refractive and UV light scattering detectors. Three SEC columns from Supelco (G6000-4000-2000 HXL) were used with triple detectors from Viscotek Co.


**Solubility:**

Poly(t-butyl acrylate) is soluble in THF, DMF and CHCl<sub>3</sub>

**SEC elugram of Sample:**

P41114-tBuA


Conc	5.7329
dn/dc	0.0650
Solvent	DMF w 0.023M LiBr
Flow Rate	0.7000
Method	PS-80K_2018-04-02-0000.vcm



Sample	Mn	Mw	Mp	Mw/Mn	IV
P41114-tBuA_01.vdt	28,797	36,842	28,454	1.279	0.4295

**DSC Thermogram of tBuA:**

Tg of poly t-butyl acrylate as function of molecular weight



**References:**

1. Ph. Teyssie, Ph. Bayard, R. Jerome, **S. K. Varshney**, and J. S. Wang, *35th IUPAC International Union of Pure & Applied Chemistry International Symposium on Macromolecules* 1994, 67.
2. R. Fayt, R. Forte, C. Jacobs, R. Jerome, T. Ouhadi, Ph. Teyssie and **S. K. Varshney**, *Macromolecules*, 1987, 20, 1442-1444.
3. Jerome, R. Forte, **S. K. Varshney**, R. Fayt, and Ph. Teyssie, "The Anionic Polymerization of Alkylacrylates: A Challenge" in the Recent Advances in Mechanistic and Synthetic Aspects of Polymerization: M. Fontanille and A. Guyot Ed., NATO ASI Series C 215, 101 (1987), CA Vol. 108, 12, 094992.
4. Ph. Teyssie, R. Fayt, C. Jacobs, R. Jerome, L. Leemans, and **S. K. Varshney** *Am. Chem. Soc., Polym. Prepr.* 1988, 28, 2, 52-53