


Sample Name: Poly (styrene-*b*-N-isopropyl acrylamide)

Sample #: P16339AA-SNIPAM

Structure:



Composition:

Mn x 10 ³ S-b-NIPAM	Mw/Mn (PDI)
74.0-b-1.0	1.10
For PS block:	T _g : 105°C
For SNIPAM block	T _g : Not distinct
* composition by HNMR	** Disribution by SEC


Synthesis Procedure:

Poly (styrene-*b*-N-isopropyl acrylamide) is prepared by anionic polymerization process. The process is proprietary at this stage.

Characterization:

The product was characterized by size exclusion chromatography (SEC) and ¹H NMR.


H-NMR spectrum of the Polymer:



SEC elugram of Sample:

P16339A-SNIPAM

Conc	3.8918
dn/dc	0.1650
Solvent	DMF w 0.023M LiBr
Flow Rate	0.7000
Method	PS-80k_2018-04-02-0000.vcm



Sample	Mn	Mw	Mp	Mw/Mn	IV
P16339A-2_01.vdt	75,602	82,992	79,568	1.098	0.2883