


Sample Name: Poly (Allyl Glycidyl ether-b-ethylene oxide-b- Ally Glycidyl ether)

Sample #: P41130-AGE-EO-AGE

Structure:



Composition:

Mn x 10 ³	PDI
2.0-b-19.5-2.0	1.05


Synthesis Procedure:

The polymer was synthesized by anionic polymerization process.

Characterization:

The molecular weight and polydispersity index of this polymer were determined by size exclusion chromatography (SEC) using a Varian liquid chromatograph equipped with a UV and refractive index detector.

¹HNMR for the polymer:



SEC elugram of the Sample:

