


Sample Name: Poly (Acrylamide)

Sample #: P41550K-AMD

Structure:



Composition:

$M_n \times 10^3$	Mw/Mn (PDI)
304.0	1.3
T_g (°C)	184

Synthesis Procedure:

Poly (Acrylamide) was synthesized by controlled radical polymerization process.

Characterization:

The polymer was characterized by size exclusion chromatography (SEC) using State-of-the-art Agilent Technologies 1260 Infinity II GPC system Equipped with triple detector:

Solvent (mobile phase) 2% acetic acid in Millipore water

Filtration: 0.45 μ Nylon Syringe Filter

Columns: Agilent three columns

Flow Rate: 1 ml/min

Injection Volume: 100 μ L

Column Temperature: 30 °C

Calibration of Instrument using PEO polymer.

Note: Polyacrylamide bearing $M_w > 1M$ are difficult to filter therefore this equipment is highly sensitive where less than 1mg/ml polymer solution can be detected by triple detector.

Solubility:

Polymer is soluble in water.

SEC Profile of the Polymer:

Agilent GPC/SEC Software

