


Sample Name: Deuterated Polystyrene (d₈)

Sample #: P41645-dPS

Structure:



Composition:

Mn x 10 ³	PDI
0.9	1.3

Synthesis Procedure:

Deuterated polystyrene-d₈ is obtained by free radical polymerization process.


Characterization:

The molecular weight and polydispersity index (PDI) are obtained by size exclusion chromatography (SEC) in THF. SEC analysis was performed on a Varian liquid chromatograph equipped with refractive and UV light scattering detectors from Viscotek Co. Three SEC columns from Supelco (G6000-4000-2000 HXL) were used.

Solubility:

Deuterated polystyrene-d₈ is soluble in DMF, THF, toluene and CHCl₃. It precipitates from methanol, ethanol, water and hexanes.

DNMR spectrum of the Sample:



SEC elugram of Homopolymer:

Agilent GPC/SEC Software

