


Sample Name: Poly (methyl methacrylate)-d₈
Atactic rich

Sample #: P41929B-dPMMA

Structure:



Composition:

Mn x 10 ³	PDI
66.0	2.0

Tg	109 °C
----	--------

Synthesis Procedure:

Deuterated poly(methyl methacrylate)-d₈ is obtained by living GTP polymerization process.


Characterization:

The molecular weight and polydispersity index (PDI) are obtained by size exclusion chromatography (SEC) in THF. SEC analysis was performed on a Varian liquid chromatograph equipped with refractive and UV light scattering detectors. Three SEC columns from Supelco (G6000-4000-2000 HXL) were used with triple detectors from Viscotek Co. ¹H NMR analysis was carried out on Varian instrument at 500MHz.

Solubility:

Deuterated poly (methyl methacrylate)-d₈ is soluble in THF, CHCl₃, toluene and dioxane. The polymer precipitates from hexanes, methanol and ethanol.

D NMR spectrum of the polymer:




SEC elugram of Homopolymer:

Agilent GPC/SEC Software

P41929B-dPMMA

Chromatogram Plot



Molecular Weight Averages

Peak	Mp (g/mol)	Mn (g/mol)	Mw (g/mol)	Mz (g/mol)	Mz+1 (g/mol)	Mv (g/mol)	PD
Peak 1	140375	65801	132693	288777	625202	246234	2.017

DSC thermogram of the Sample:

Sample: P19315-dMMA
 Size: 6.0000 mg

DSC

File: P19315.001

