


Sample Name:

**Deuterated poly(methyl vinyl ether)-d6**

Sample #: **P42155-d6MVE**

**Structure:**




**Composition:**

$M_n \times 10^3$ (g/mol)	$M_w/M_n$
14.0	1.10

Glass transition temperature (T <sub>g</sub> ):	-30 °C
---	--------

**Synthesis procedure:**

Deuterated [d6] poly (methyl vinyl ether) was obtained by living cationic polymerization. The reaction scheme is shown below:




**Characterization:**

The product was characterized by size exclusion chromatography (SEC), <sup>1</sup>HNMR and DNMR.


**Solubility:**

Deuterated poly (methyl vinyl ether) is soluble in Acetone and Methanol.

**DNMR spectrum of the Sample in CHCl<sub>3</sub>:**




**HNMR spectrum of the sample in CdCl<sub>3</sub>:**



**SEC elugram of the Sample:**

Agilent GPC/SEC Software



**DSC thermogram (2<sup>nd</sup> heating scan, 10°C/min):**

