


Sample Name: Deuterated Poly(methylacrylate)
Ester group deuterated

Sample #: P42726A-d3MA

Structure:



Composition:

Mn x 10 ³	PDI
511.0	1.2

Synthesis: The polymer was Prepared by radical process.


Characterization:

The molecular weight and polydispersity index (PDI) are obtained by size exclusion chromatography (SEC) in THF. SEC analysis was performed on a Varian liquid chromatograph equipped with refractive and UV light scattering detectors. Three SEC columns from Supelco (G6000-4000-2000 HXL) were used with triple detectors from Viscotek Co.


Solubility:

Deuterated Poly(methyl acrylate) is soluble in THF, CHCl₃ and Toluene.


¹H-NMR spectrum of the monomer:




D-NMR spectrum of the polymer:



¹H-NMR spectrum of the polymer:



SEC elugram of the Sample:



References:

- Ph. Teyssie, Ph. Bayard, R. Jerome, S. K. Varshney, and J. S. Wang, *35th IUPAC International Union of Pure & Applied Chemistry International Symposium on Macromolecules* 1994, 67.
- R. Fayt, R. Forte, C. Jacobs, R. Jerome, T. Ouhadi, Ph. Teyssie and S. K. Varshney, *Macromolecules*, 1987, 20, 1442-1444.

3.Jerome, R. Forte, **S. K. Varshney**, R. Fayt, and Ph. Teyssie, "The Anionic Polymerization of Alkylacrylates:A Challenge" in the Recent Advances in Mechanistic and Synthetic Aspects of Polymerization: M. Fontanaille and A. Guyot Ed., NATO ASI Series *C 215,101 (1987)*, *CA Vol. 108, 12, 094992.*

4.Ph. Teyssie, R. Fayt, C. Jacobs, R. Jerome, L. Leemans, and **S. K. Varshney** *Am. Chem. Soc.,Polym. Prepr.* 1988, 28, 2, 52-53