


Sample Name: Poly(methyl acrylate)

Sample #: P43041D-MA

Structure:



Composition:

Mn x 10 ³	PDI
6.0	1.28


Synthesis Procedure:

The polymer was synthesized by GTP -polymerization.

Characterization:

The polymer was characterized by size exclusion chromatography (SEC).

SEC profile of the Sample:



Peak	Mp (g/mol)	Mn (g/mol)	Mw (g/mol)	Mz (g/mol)	Mz+1 (g/mol)	Mv (g/mol)	PD
Peak 1	7464	5937	7641	9309	10947	8859	1.287

Processing Parameters