


Sample Name:

Random Copolymer Poly (styrene-co-butadiene)

Sample #: **P43138-SBdran**

Structure:



Composition:

Mn x 10 ³ PS-co-PBd	PDI
37.0	1.01
T _g for random polymer	-25°C
Styrene (wt): 28%	

Synthesis Procedure:

Random Copolymer Poly (styrene-co-butadiene) is prepared by radical polymerization of styrene and butadiene.

Characterization:

The polymer was analyzed by size exclusion chromatography (SEC) to obtain the molecular weight and polydispersity index (PDI). The copolymer composition was calculated from ¹H-NMR spectroscopy.


Thermal analysis:

Thermal analysis of the samples was carried out on a TA Q100 differential scanning calorimeter at a heating rate of 10°C/min. The midpoint of the slope change of the heat flow plot of the second heating scan was considered as the glass transition temperature (T_g).


Solubility:

Random Copolymer Poly (styrene-co-butadiene) is soluble in CHCl₃, THF, DMF, toluene and precipitated out from methanol.

SEC elugram of the random copolymer:



H NMR spectrum of the Sample:



DSC thermogram of the sample:

