


Sample Name:

Amino terminated Polystyrene-b-butadiene (rich in 1,2-addition)-b-methylmethacrylate)

Sample #: P11138B-NH2-SBdMMA



Structure:

Composition:

Mn x 10 ³		PDI	
NH2-S-b-Bd-b-MMA		1.34	
35.0-b-13.0-b-112.0			
T _g for PS block	T _g for Bd block	T _g for MMA block	
100 oC	Not found	132°C	

Synthesis Procedure:

The triblock polymer is synthesized by living anionic polymerization with sequence addition of styrene, butadiene (Bd), followed by methyl methacrylate (MMA). Amino protected lithium based initiator was used. For details you may read our published work.

Varshney, S. K.; Song, Z.; Zhang, Jian-Xin.; Jerome, Robert. Rapid Communication; J. Polym. Sci. Part A, 2006, 44, 3400.

Characterization:

Size exclusion chromatography (SEC): Varian liquid chromatograph equipped with UV and refractive detector. SEC columns from Supelco were used with THF as the eluent.. The molecular weights and the polydispersity index were calculated.


Thermal analysis:

Thermal analysis of the samples was carried out on a TA Q100 differential scanning calorimeter at a heating rate of 10°C/min. The midpoint of the slope change of the heat flow plot of the second heating scan was considered as the glass transition temperature (T_g).

Solubility:

Polymer is soluble in THF, toluene, acetone and CHCl₃. The polymer readily precipitates from hexanes, ether and water.


¹H-NMR Spectrum of the product




SEC of the polymer:

Sample ID: P11138-SBdMMA


Concentration (mg/mL)	6.9877
Sample dn/dc (mL/g)	0.1050
Method File	PS80K-Oct-2012-0002.vcm
Column Set	3x PL 1113-6300
System	System 1



Sample	Mn (Da)	Mw (Da)	Mp (Da)	Mw/Mn	IV (dL/g)
P11138-SBdMMA_2012-10-24_13:15:56_01.v	152,909	208,115	163,249	1.361	0.6224



P11138B-NH2SBdMMA



Size exclusion chromatography of NH2-polystyrene-b-butadiene (rich in 1,2 addition)

- First bioPoly styrene, M_n=35,000, M_w=37,800, PI=1.08
- Poly(styrene-b- polybutadiene):PS(35,000)-b-PBd(13,000), PI=1.3
- Poly(styrene-b-Polybutadiene-b-MMA) Mn: 35,000-b-13,000-b-112,000 Mw/Mn : 1.34