


**Sample Name:** Poly(dimethylsiloxane),  $\alpha$ ,  $\omega$ -bis (hydroxy [carbinol])-terminated

*Propyl Ethoxy linker*

**Sample #:** P42754-DMS2OH

### Structure:



### Composition:

Mn x 10 <sup>3</sup>	PDI
1.2	1.2


### Synthesis Procedure:

Dihydroxyl (carbinol) terminated poly (dimethyl siloxane) was prepared by living anionic polymerization of hexamethyl cyclotrisiloxane. Silanol end groups were then modified to carbinol end groups.

### Characterization:


The molecular weight and polydispersity index of this polymer were determined by size exclusion chromatography (SEC) using a Varian liquid chromatograph equipped with a UV and refractive index detector. Eluent was toluene at 35 °C.

### <sup>1</sup>H-NMR spectrum of the PDMS end functionalized with Carbinol to determine molecular weights by HNMR:



### SEC profile of the Sample:

**P42754-DMS2OH carbinol**



— Polydimethylsiloxane  $M_n=1,200$ ,  $M_w=1,500$ ,  $PI=1.2$

### Reference:

1. J.X. Zhang, S.K. Varshney, "Simple Approach for the Scale-up Production of Block Copolymer of Polydimethylsiloxane with (Meth)acrylic Ester Monomers" Designed Monomers and Polymers, 2002, 1, 79.