


Sample Name: Poly(styrene-co-4-allyl styrene), random

Sample #: P41466A-SSAllyl

Structure:



Composition:

Mn x 10 ³	AllylStyrene, mol%	Mw/Mn
8.8	9.0%	1.34

Synthesis Procedure:

Poly(styrene-co-[4-allylstyrene]) is synthesized by copolymerization of styrene and 4-allyl styrene.


Characterization:

The molecular weight and polydispersity index (PDI) of polymers are obtained by size exclusion chromatography. The composition is determined by NMR.


Solubility:

Poly(styrene-co-[4-allylstyrene]) is soluble in THF, DMF, chloroform, and Toluene. It precipitates from hexane or methanol.

HNMR spectrum of Polymer:



SEC elugram of Polymer:



HNMR of Allyl Styrene:

