Sample Name: **Deuterated Poly(tert.butylacrylate) Ester group protonated**

Sample #: **P43765-d3tBuA**

Structure:



Composition:

Mn x 10^3	PDI
4.0	1.3
Mp: 6.0	

Characterization:

The molecular weight and polydispersity index (PDI) are obtained by size exclusion chromatography (SEC) in THF. SEC analysis was performed on a Varian liquid chromatograph equipped with refractive and UV light scattering detectors. Three SEC columns from Supelco (G6000-4000-2000 HXL) were used with triple detectors from Viscotek Co.

Solubility:

Deuterated Poly(ter.Butyl acrylate) is soluble in THF, CHCl3, and Toluene.

HNMR spectrum of the monomer:



D NMR spectrum of the monomer:



SEC elugram of the Sample:



References:

1. Ph. Teyssie, Ph. Bayard, R. Jerome, **S. K. Varshney**, and J. S. Wang, *35th IUPAC International Union of Pure & Applied Chemistry International Symposium on Macromolecules" 1994, 67.*

2. R. Fayt, R. Forte, C. Jacobs, R. Jerome, T. Ouhadi, Ph. Teyssie and **S. K. Varshney,** *Macromolecules, 1987, 20, 1442-1444.*

3. Jerome, R. Forte, **S. K. Varshney**, R. Fayt, and Ph. Teyssie, "The Anionic Polymerization of Alkylacrylates:A Challenge" in the Recent Advances in Mechanistic and Synthetic Aspects of Polymerization: M. Fontanaille and A. Guyot Ed., NATO ASI Series *C 215,101 (1987), CA Vol. 108, 12, 094992.*