


**Sample Name: Deuterated  
Poly(tert.butylacrylate) Ester group protonated**

**Sample #: P43800A-d3tBuA**

**Structure:**



**Composition:**

Mn x 10 <sup>3</sup>	PDI
10.0	1.5


**Characterization:**

The molecular weight and polydispersity index (PDI) are obtained by size exclusion chromatography (SEC) in THF. SEC analysis was performed on a Varian liquid chromatograph equipped with refractive and UV light scattering detectors. Three SEC columns from Supelco (G6000-4000-2000 HXL) were used with triple detectors from Viscotek Co.


**Solubility:**

Deuterated Poly(ter.butyl acrylate) is soluble in THF, CHCl<sub>3</sub>, and Toluene.


**HNMR of the monomer:**



**D NMR of the monomer:**



**SEC elugram of the Sample:**



**References:**

1. Ph. Teyssie, Ph. Bayard, R. Jerome, **S. K. Varshney**, and J. S. Wang, *35th IUPAC International Union of Pure & Applied Chemistry International Symposium on Macromolecules* 1994, 67.
2. R. Fayt, R. Forte, C. Jacobs, R. Jerome, T. Ouhadi, Ph. Teyssie and **S. K. Varshney**, *Macromolecules*, 1987, 20, 1442-1444.
3. Jerome, R. Forte, **S. K. Varshney**, R. Fayt, and Ph. Teyssie, "The Anionic Polymerization of Alkylacrylates: A Challenge" in the Recent Advances in Mechanistic and Synthetic Aspects of Polymerization: M. Fontanille and A. Guyot Ed., NATO ASI Series C 215, 101 (1987), CA Vol. 108, 12, 094992.