


Sample Name:

**Poly(styrene-co-4-vinylbenzyl chloride), ( $\alpha$ -hydroxy,  $\omega$ -TEMPO)-terminated**

Sample #: **P43990C-SClMeSranOHT**

**Structure:**




**Composition:**

Mn x 10 <sup>3</sup>	Mw/Mn (PDI)
19.0	1.45
P4ClMeS = 25 mol%	

**Synthesis Procedure:**

Hydroxy terminated poly(styrene-co-4-Chloromethyl Styrene) is prepared by stable free radical polymerization at 135°C. The reaction scheme is shown below:




**Characterization:**

An aliquot of the copolymer was analyzed by size exclusion chromatography (SEC) to obtain the molecular weight and polydispersity index (PDI), the instrument calibrated by Polystyrene standards. The chemical composition was calculated from <sup>1</sup>H-NMR spectroscopy by comparing the peak area of the phenyl protons at 6.8-7.4 ppm with the peak area of benzyl at 4.5 ppm.


**Solubility:**

Polymer is soluble in THF, DMF, Toluene and chloroform. Precipitate from methanol and Hexanes.

**<sup>1</sup>H NMR spectrum of the Sample:**



**SEC profile of the random copolymer:**



Peak	Mp (g/mol)	Mn (g/mol)	Mw (g/mol)	Mz (g/mol)	Mz+1 (g/mol)	Mw (g/mol)	PDI
Peak 1	28422	18987	27782	39042	52996	36651	1.463