


Sample Name: Poly(N-vinyl imidazole)

Sample#: P44412C-VIMDZ

Structure:




Composition:

$M_n \times 10^3$	PDI
66.0	4.5

Synthesis Procedure:

Polymer is obtained by RAFT polymerization process using following RAFT.



Characterization:

The molecular weight and polydispersity index (PDI) of polymer is obtained by size exclusion chromatography in aqueous system (water as eluent with 0.1% trifluoroacetic acid and 0.2M NaCl). The columns were calibrated with poly ethylene glycol.

Thermal analysis

Thermal analysis of the samples was carried out on a TA Q100 differential scanning calorimeter at a heating rate of 10°C/min. The midpoint of the slope change of the heat flow plot of the second heating scan was considered as the glass transition temperature (T_g).

Solubility:

Polymer is soluble in water, and methanol. It precipitated out from hexane, and ether.

SEC elugram of Homopolymer:

