

# Product Profile

## Identification

**Product Name:** Poly(styrene-b-4-vinyl-pyridine)

**Product Lot Number:** P9873-R-S4VP

**CAS #:** 26222-40-2

**Product Chemical Architecture:**



**Composition:**

| Composition (S-b-4VP)        | 138,000-b-46,000 |
|------------------------------|------------------|
| 4VP mole%                    | 24.8             |
| Mn (g/mole)                  | 184,000          |
| Mw (g/mole)                  | 190,000          |
| Mw/Mn                        | 1.03             |
| dn/dc (mL/g) in DMF at 35 °C | 0.162            |

## Method of Synthesis

The polymer is synthesized by anionic polymerization process.

**Solubility in different solvents:**

|                          |                        |                   |   |
|--------------------------|------------------------|-------------------|---|
| THF                      | Depends on composition | DMF               | ✓ |
| Alcohol                  | Depends on composition | CHCl <sub>3</sub> | ✓ |
| Toluene <sub>(hot)</sub> | X                      | Water             | X |


## Validation of Architecture

### A. Gel Permeation Chromatography (GPC), SEC Profile:

Molecular weights were determined by Malvern OmniSec Reveal & Resolve GPC/SEC System equipped with Triple detector (RI, Viscometer, RALS 90° and LALS 7°) and two columns (PSS, SDV, 8x300 mm). DMF with 0.023M LiBr was the eluent. The flow rate was 0.7 ml/min.

Polymer Source

Malvern Panalytical



**B. NMR ( $^1\text{H}$ NMR) of S4VP in  $\text{CDCl}_3$ , 500 MHz**

P9873-R  
Company Polymer Source  
1d\_proton\_16scans CDCI3 {D:\Polymer\_Source} PSource 43

