


Sample Name: Poly(glycidyl methacrylate)

Sample #: P11317-GMA

Structure:




Composition:

$M_n \times 10^3$	PDI
28.0	1.4

Synthesis Procedure:

Poly(glycidyl methacrylate) is obtained by living anionic polymerization of glycidyl methacrylate. The reaction scheme used for the polymer synthesis is shown below:




Characterization:

The molecular weight and polydispersity index (PDI) of Poly(glycidyl methacrylate) are obtained by size exclusion chromatography.

Solubility:

Poly(glycidyl methacrylate) is soluble in THF, $CHCl_3$, toluene and dioxane. The polymer precipitates from cold methanol and ethanol.

SEC of Homopolymer:
P11317-GMA



Size Exclusion Chromatography of Poly(glycidyl methacrylate)
 $M_n=28,000$, $M_w=39,600$, $PI=1.4$