


Sample Name:

Poly(methacrylic acid) rich in Atactic contents

Sample #: P14096-MAA

(rich in atactic)

Structure:**Composition:**

Mn x 10 ³	PDI
165.0	1.15
T _g (°C)	165

Synthesis Procedure:

Poly(methacrylic) is synthesized by RAFT process

Characterization:


The molecular weight and polydispersity index (PDI) of Poly(methacrylic) are obtained by size exclusion chromatography in DMF at 45 °C.

Thermal analysis:


Thermal analysis of the samples was carried out on a TA Q100 differential scanning calorimeter at a heating rate of 10 °C/min. The midpoint of the slope change of the heat flow plot of the second heating scan was considered as the glass transition temperature (T_g).

Solubility:


Polymer is soluble in methanol and ethanol.

HNMR of the Polymer**SEC of the homopolymer:**

P14096-MAA



M_n=165,000, M_w=189,000, PI=1.15

Thermogram for the polymer:**References:**

S. K. Varshney, Z. Gao, Xing Fu Zhong, A. Eisenberg "Effect of Lithium Chloride on the "Living" Polymerization of tert-Butylmethacrylate and Polymer Microstructure Using Monofunctional Initiators" Macromolecules, 1994, 27, 1076.