


Sample Name: Carboxy-terminated Polybutadiene (1,4-rich microstructure)

Sample #: P1442-BdCOOH

Structure:




Composition:

Mn x 10 ³	PDI
11.0	1.03
COOH functionality:	98 %
PBd 1,4-addition:	60 %

Synthesis Procedure:

1,4-addition carboxy-terminated polybutadiene was prepared by anionic living polymerization of butadiene in non-polar media (or in presence of 10% diethyl ether), followed by termination of the polymerization with dried CO₂. The scheme of the reaction is presented below:



Characterization:

The molecular weight and polydispersity index (PDI) are obtained by size exclusion chromatography (SEC) in THF. SEC analysis was performed on a Varian liquid chromatograph equipped with refractive and UV light scattering detectors. Three SEC columns from Supelco (G6000-4000-2000 HXL) were used with triple detectors from Viscotek Co.


Functionality: The microstructure of the polymer was calculated by proton NMR spectroscopy.

Microstructure: The ratio between 1,4- and 1,2-addition was calculated by ¹H NMR spectroscopy.

Solubility:


COOH terminated polybutadiene is soluble in DMF, THF, toluene, hexane, cyclohexane and CHCl₃. It precipitates from methanol, ethanol and water.

¹H NMR spectrum:



Ratio 1,4- to 1,2-addition = 0.6 : 0.4

SEC elugram:



Size exclusion chromatography of polybutadiene.

M_n=11000, M_w=11300, PI=1.03, functionality=0.98%