


Sample Name: **Poly(Acrylic acid)**

Sample #: P14582-AA (RAFT)

Structure:




Composition:

Mn x 10 ³	Mw/Mn (PDI)
123.0	1.25

Synthesis Procedure:

Poly(acrylic acid) is synthesized by RAFT polymerization of acrylic acid using 2,2'-azobisobutyrate (CAS 2589-57-3) as initiator and xanthate as chain transfer agent:




Characterization:

Polyacrylic acid and analyzed by size exclusion chromatography (SEC) to obtain the molecular weight and polydispersity index (PDI) using water containing 0.1M NaNO₃ and 0.01M NaH₂PO₄ and 4 Vol% acetonitrile as eluent. The molecular weigh can also be verified after converting poly acrylic acid to poly n-butyl acrylate by transesterification process and anal sizing the polymers by SEC in organic phase

Solubility: Polymer is soluble in water.

¹H-NMR Spectrum of the Polymer:




SEC was carried out to convert PAA into Poly n-Butylacrylate to determine molecular weight of the poly acrylic acid

SEC of Sample of the polymer:

Sample ID: P14582-nBuA

Concentration (mg/mL)	5.5294
Sample dn/dc (mL/g)	0.0640
Method File	PS80K-Apr-2013-0000.vcm
Column Set	3x PL 1113-6300
System	System 1



Sample	Mn	Mw	Mp	Mw/Mn	IV
P14582-nBuA_01.vdt	228,953	288,095	296,224	1.258	1.3878

