


Sample Name: Anthracene Terminated Poly(methyl methacrylate)

Sample #: P14993A-MMA-An

Structure:




Composition:

Mn x 10 ³	PDI
20.0	1.10

Microstructure (S:H:I)	73:23:4
------------------------	---------

Synthesis Procedure:

The polymer was synthesized by anionic process :



Characterization:


The polymer was characterized by size exclusion chromatography (SEC) and ¹H NMR.

Functionality: functionality of the obtained polymer was determined by proton NMR.

Solubility:

Anthracene terminated PMMA is soluble in DMF, THF, toluene, and CHCl₃. It precipitates from methanol, hexane and water.

¹H NMR spectrum of polymer:



SEC elugram:

Sample ID P14993A-MMAAn

Concentration (mg/mL)	0.5921
Sample dn/dc (mL/g)	0.0940
Method File	PS80K-March2016-0001.vcm
Column Set	3x PL 1113-6300
Solvent	THF

