


Sample Name:
Poly-(NN-dimethylaminoethyl methacrylate)

Sample #: **P16075C-DMAEMA**

Structure:



Composition:

Mn x 10 ³	19.0
PDI	1.34

Synthesis:

Poly(N,N-dimethylaminoethyl methacrylate) was synthesized by atom transfer radical polymerization.


Characterization:

The molecular weight and polydispersity index (PDI) of Poly(N,N-dimethylaminoethyl methacrylate) were obtained by size exclusion chromatography (SEC).


Solubility:

The polymer is soluble in THF, DMF, and Acetone.


ATRP reagent used for polymerization:



¹H NMR spectrum of the ATRP reagent in CDCl₃:




¹H NMR Spectrum of the homopolymer P16075C:



SEC elugram of the polymer:

P16075-C-DMAEMA

Conc (mg/mL)	9.2496
dn/dc (mL/g)	0.0840
Method	PS80k-July22-2016-0000.vcm
Solvent	DMF w/0.023M LiBr
Column	PSS



Sample	Mn	Mw	Mp	Mw/Mn	IV
P16075C2_01.vdt	18,975	25,463	23,337	1.342	0.1536