


**Sample Name:**

**Deuterated Polystyrene ( $d_8$ )-Methyl methacrylate (protonated)**

**Sample #: P1728-dPSMMA****Structure:****Composition:**

Mn x 10 <sup>3</sup> (dPS-b-MMA)	PDI
15.0-b-11.0	1.10
T <sub>g</sub> for PS block	105°C
T <sub>g</sub> for MMA block	127°C

**Synthesis Procedure:**

Deuterated poly(styrene ( $D_8$ )-b-methyl methacrylate) is prepared by living anionic polymerization in THF at -78°C using sec.BuLi initiator in the presence of LiCl. Deuterated Polystyrene macroanions were end capped with a unit of diphenyl ethylene (DPE) before adding methylmethacrylate (MMA) monomer. For further details please consult our publications.<sup>1-5</sup>

**Characterization:**

The molecular weight and polydispersity index (PDI) are obtained by size exclusion chromatography (SEC) in THF. SEC analysis was performed on a Varian liquid chromatograph equipped with refractive and UV light scattering detectors from Viscotek Co. Three SEC columns from Supelco (G6000-4000-2000 HXL) were used.


Thermal analysis of the samples was carried out using a differential scanning calorimeter (TA Q100) at a heating rate of 15°C/min. The inflection glass transition temperature (T<sub>g</sub>) of the sample has been considered.

**Solubility:**

Deuterated polystyrene- $d_8$ MMA is soluble in DMF, THF, toluene and CHCl<sub>3</sub>. It precipitates from methanol, ethanol, water and hexanes.


**SEC of the product:**

P1728-dPSMMA



Size exclusion chromatography of deuterated polystyrene-b-poly(methyl methacrylate)

— Deuterated ( $d_8$ )polystyrene, M<sub>n</sub>=15000, M<sub>w</sub>=16300, PI=1.09  
— Block Copolymer DPS(15000)-b-PMMA(11000), PI=1.10

**Thermogram for the diblock polymer:****References for further information:**

1. S. K. Varshney, R. Fayt, Ph. Teyssie, and J.P. Hautekeer US Patent 5,264,527 (1993)
2. Ph. Teyssie, Ph. Bayard, R. Jerome, S. K. Varshney, and J. S. Wang, *35th IUPAC International Union of Pure & Applied Chemistry International Symposium on Macromolecules* 1994, 67.
3. Ph. Teyssie, R. Fayt, J. P. Hautekeer, C. Jacobs, R. Jerome, L. Leemans and S. K. Varshney *Makromolekular Chemie, Macromol. Symp.*, 1990, 32, 61-73.
4. S. K. Varshney, J. P. Hautekeer, R. Fayt, R. Jerome, and Ph. Teyssie *Macromolecules*, 1990, 23, 2618-2622.
5. R. Jerome, R. Forte, S. K. Varshney, R. Fayt, and Ph. Teyssie. "The Anionic Polymerization of Alkylacrylates:A Challenge" in the Recent Advances in Mechanistic and Synthetic Aspects of Polymerization: M. Fontanaille and A. Guyot Ed., NATO ASI Series C 215, 101 (1987), CA Vol. 108, 12, 094992.