


Sample Name: Bromo terminated
Poly(Styrene-b-methyl methacrylate) diblock copolymer
(Anionic process) PMMA : Syndiotactic rich
Sample #: P10061-SMMA-Br
Structure:



Composition:

Mn × 10 ³ (S-b-MMA-br)	PDI
7.0-b-9.0	1.15
Microstructure of PMMA block	S:H:I contents 78:10:2
T _g for PS block: Not distinct	T _g for MMA block: 100 °C

Synthesis Procedure:

Poly(styrene-b-methylmethacrylate-b-styrene) is prepared by using anionic and controlled process.

Characterization:

The molecular weight and polydispersity index of this polymer were determined by size exclusion chromatography (SEC) using a Varian liquid chromatograph equipped with a UV and refractive index detector.

Thermal analysis:


Thermal analysis of the samples was carried out on a TA Q100 differential scanning calorimeter at a heating rate of 10°C/min. The midpoint of the slope change of the heat flow plot of the second heating scan was considered as the glass transition temperature (T_g).

Solubility:

Polymer is soluble in THF, toluene and CHCl₃. It precipitates from methanol, ethanol, water and hexanes.


NMR of the initiator:

PS-MMA Br diblock copolymer:



SEC of Sample:


P10061-SMMABr



Size Exclusion Chromatography of:

— PS first block, M_n=7,000 Mw: 8000 PI=1.15
 — SMMA, the Diblock PS(7,000)-b-PMMA(9000) PI=1.15

DSC thermogram for MMA block:



Reference:

S.K. Varshney, P. Kesani, N. Agarwal, J. Xin. Zhang, and M. Rafailovich. Synthesis of ABA type thermoplastic elastomers based on Polyacrylates, *Macromolecules*, 1999, 32, 235.