

Product Profile

Identification

Product Name: Poly(ethylene glycol) methyl ether


Synonym(s): PEO, PEG

Linear Formula: $\text{H}(\text{OCH}_2\text{CH}_2)_n\text{OCH}_3$

CAS: 25322-68-3

Product Lot Number: P18089-EGOCH3

Product Chemical Architecture:



Composition:

Mn (g/mole)	65,000
MW (g/mole)	88,000
Mw/Mn	1.36
dn/dc (mL/g)	0.132 in water

Method of Synthesis

The polymer is prepared by living anionic polymerization process.

Solubility in different solvents

THF	√	DMF	√
Methanol	√	CHCl ₃	√
Toluene	X	DMSO	√

Validation of Architecture

A. Gel Permeation Chromatography (GPC), SEC- Profile:


Molecular weights were determined by Malvern OmniSec Reveal & Resolve GPC/SEC System equipped with Triple detector (RI, Viscometer, RALS 90° and LALS 7°) and two columns (A600M General Mixed 300×7.5 mm, Viscotek). 0.25 M NaNO₃ + 0.01M NaH₂PO₄ (PH=7) in water was the eluent. The flow rate was 1.0 ml/min.

Polymer Source

Malvern Panalytical



Raw Data Chart






Results (Rows)

Injection Name	RV (mL)	Mn (g/mol)	Mw (g/mol)	Mp (g/mol)	Mz (g/mol)	Mw/Mn
P18089, Injection 1, Peak 1	16	64,721	87,712	99,249	183,758	1.355

B. Thermal analysis results:

Sample	T _m (°C)	T _c (°C)	T _g (°C)
Typical PEO sample (Mn over 50k Da)	66	43	-43



C. NMR (HNMR) OF PEO in DMSO, general

